



**LUMBER WORLD**

'A Destination for your Imagination'

# COMMERCIAL PLYWOOD

From whispering woods to stalwart walls, a saga etched in grain. Logs yield their secrets, each veneer a sun-kissed note. Heat and pressure, the architects of strength, weave their magic. Born not of meekness, but of a thousand whispers, commercial plywood rises, ready to build your dreams, one sturdy sheet at a time.





## COMMERCIAL PLYWOOD

PLYWOOD TYPE		18 MM PLYWOOD		
Plywood Composition	Face Back		0.70 mm x 2	
	Short Core		3.40 mm x 3	
	Long Core		3.40 mm x 2	
Specices	–		medium light hardwood	
Panel size	–		1220 mm x 2440 mm	
No of plies	–		7	
Bonding/adhesive	–		MR MELAMINE	
Property	Test Method		Value Of Test	
Moisture content	en 323		11.50%	
Density	en 322		675 kg/m3	
Modulus of rupture (mor)	parallel		35.42	N/MM2
	perpendicular		47.70	N/MM2
Modulus of elasticity (mode)	parallel	en 323	4288	N/MM2
	perpendicular		6441	N/MM2
Class grade			F 20/30 E 40/60	
Bonding quality ( shear strength)		en 323	PASSED RATE = 94%	REQUIREMENT >90%