



LUMBER WORLD

'A Destination for your Imagination'

FILM FACED SHUTTERING PLYWOOD

In the construction theater, film-faced shuttering plywood emerges as a resilient virtuoso, adorned in a celestial film of phenolic resin or melamine. Like a painter's stroke, this film layer grants it a durable shield against wear and tear. Silent in its support for formwork, it provides a smooth stage for concrete pours, a sculptor's chisel in the realm of construction dreams.

A versatile deity in the marketplace, it comes in various sizes, a poetic crescendo valued for its strength and balletic resilience amidst the scaffolding of durability and environmental defiance.





FILM FACED SHUTTERING PLYWOOD

SPECIFICATIONS

ITEM		UNIT	Ref.Document	Value of Test
Moisture Content		%	EN 322	6-12
Density		kg/m ³	EN 323	≥ 530
Bonding Quality	Bonding Quality Damage Rate	Mpa %	EN 314	x max 172, xmin:085 60%
Moe	Longitudinal Lateral	N/mm ²	EN 310	≥ 5700 ≥ 5300
Mor	Longitudinal Lateral	N/mm ²	EN 310	≥ 40 ≥ 30
Film	Dyer Brand	kg/m ³	EN 313	180
Water Boiled		/	/	≥ 48 hours
Water Boiled		/	/	≥ 10
Number Of Piles				11 ply +2 layers film